



A WILSONART COMPANY

SOLID PHENOLIC COMPACT WORKSURFACES

Solid Phenolic Compact (SPC) by Durcon is a functional and decorative worksurface for high impact, heavy use environments such as laboratories and other facilities in the education, healthcare and R&D segments. Engineered for horizontal and vertical applications like countertops, shelving and partitions, these durable self-supporting surfaces are available in three grades, several thicknesses, and many color options.

SPC GRADES



Chemical Resistance Grade SPC-CR includes a specially Electron Beam Cured (EBC) layer, providing industry leading resistance to many acids, solvents, reagents & cleaning agents.
Note: not available in 4' x 8' or 4' x 10' sheets.

APPLICATIONS

- Laboratory settings
- Reagent shelving
- Prep room worksurfaces
- Mobile carts

COLORS

Durcon Graphite*	Steel Grey
	Carbon Black
Durcon Gray*	Glacier White

*color-match Epoxy



Fire-rated SPC is thick Standard Grade with fire retardant properties, used where building codes require a rating of **Class A (or 1)**.

- Elevator cabs
- Stairwells
- Hospitals
- Airports
- Marine/Aerospace

Available colors for both Fire-rated and Standard Grades:

Fashion Grey	Black	Designer White
--------------	-------	----------------

In addition to our three signature colors above, Fire-rated and Standard grades are available in 100s of other options.



Standard Grade SPC is a surfacing solution designed for *all-around* use, available in a selection of smart colors, plus the option for custom colors of graphic designs.

- Partitions
- Cabinetry
- Assembly stations
- Doctor's offices

To view the full selection, visit www.wilsonart.com/compact, select a color option, then look for **Finish 60** under the Pattern Availability section. Finish 60 indicates that a color is available in both SPC Fire-rated & Standard grades.

If you are not sure about a specific color or need help, please contact a Customer Service associate for clarification.

THICKNESS & SIZES



Thicknesses available:
0.25" 0.375" 0.5"
0.75" 1.0"

Samples available in 1.0"

Sheets sizes available:
4' x 8' 4' x 10' (Standard & Fire-rated only)
5' x 8' 5' x 10' 5' x 12' (All grades)

SEE IT WITH VISUALIZER

Design with SPC in real-time using Durcon's Visualizer tool.
www.durcon.visualizapro.com



SAMPLES & ORDERS

To request samples of Durcon SPC, please reach out to your regional Durcon representative, or contact our Customer Service team at:

✉ samples@durcon.com
☎ 1-512-595-8000

CERTIFICATIONS & ORGANIZATIONS



TESTING RESULTS FOR SPC CHEMICAL RESISTANCE GRADE

CHEMICAL & STAIN RESISTANCE TESTING

CHEMICAL Tested	TEST method	SPC-CR RATING
Acetate, Amyl	A	0
Acetate, Ethyl	A	0
Acetic Acid 98%	B	0
Acetone	A	0
Acid Dichromate 5%	B	1
Alcohol, Butyl	A	0
Alcohol, Ethyl	A	0
Alcohol, Methyl	A	0
Ammonium Hydroxide 28%	B	1
Benzene	A	0
Carbon Tetrachloride	A	0
Chloroform	A	0
Chromic Acid 60%	B	1
Cresol	A	1
Dichloroacetic Acid	A	1
Dimethylformamide	A	0
Dioxane	A	0
Ethyl Ether	A	0
Formaldehyde 37%	A	0
Formic Acid 90%	B	1
Furfural	A	0
Gasoline	A	0
Hydrochloric Acid 37%	B	0
Hydrofluoric Acid 48%	B	1
Hydrogen Peroxide 30%	B	0
Iodine, Tincture of	B	1
Methyl Ethyl Ketone	A	1
Methylene Chloride	A	0
Monochlorobenzene	A	1
Naphthalene	A	0
Nitric Acid 20%	B	0
Nitric Acid 30%	B	0
Nitric Acid 70%	B	0
Phenol 90%	A	1
Phosphoric Acid 85%	B	0
Silver Nitrate, Saturated	B	0
Sodium Hydroxide 10%	B	0
Sodium Hydroxide 20%	B	0
Sodium Hydroxide 40%	B	0
Sodium Hydroxide Flake	B	0
Sodium Sulfide, Saturated	B	0
Sulfuric Acid 33%	B	0
Sulfuric Acid 77%	B	0
Sulfuric Acid 96%	B	0
Sulfuric Acid 77%, and Nitric Acid 70%, equal parts	B	0
Toluene	A	0
Trichloroethane	A	0
Xylene	A	0
Zinc Chloride, Saturated	B	0

After 24-hours exposure, areas are washed with water, then a detergent solution and finally with isopropyl alcohol. Materials are then rinsed with distilled water and dried with a cloth. Samples are numerically rated as:

0 = No effect, 1 = Excellent, 2 = Good, 3 = Fair

TEST METHOD A

For volatile chemicals. A cotton ball saturated with the test chemical was placed in a one ounce bottle (10mm x 75mm test tube or similar container). The container was inverted on the test material surface for a period of 24 hours. Temperature of test: 73° +/-4°F (23° +/-2°C). This method was used for the organic solvents.

TEST METHOD B

For non-volatile chemicals. Five drops (1/4cc) of the test chemical were placed on test material surface. The chemical was covered with a watch glass (25mm) for a period of 24 hours. Temperature of test: 73° +/-4°F (23° +/-2°C). This method was used for all chemicals listed below other than the solvents.

PHYSICAL PROPERTIES TESTING

TEST Procedure	PROPERTY Description	SPC-CR RESULT Unit of Measurement
EN 438-2:10	Resistance to Surface Wear	≥150 Revolutions (Initial Point)
EN 438-2:21	Resistance to Impact	0.4 Indention Diameter (mm) No Cracks or Scoring
EN 438-2:25	Resistance to Scratch	5 Rating (Based on Load)
EN 438-2:16	Resistance to Dry Heat (320°F)	5 Appearance (Rating)
EN 12721	Resistance to Wet Heat (212°F)	5 Appearance (Rating)
EN 438-2:12	Resistance to Immersion in Boiling Water	5 Appearance (Rating) 0.4 Mass Increase % 1.9 Thickness Increase %
EN 438-2:17	Dimensional Stability in Elevated Temperature	0.05 Longitudinal (Parallel) % 0.05 Transversal (Perpendicular) %
EN 438-2:26	Resistance to Staining (Appearance Rating)	5 Acetone 5 NaOH 5 Hydrogen Peroxide (H ₂ O ₂ 3%)
ASTM G53/ EN 4382:27	Resistance to Color Change	5 Rating (Grey Wool Scale) >6 Rating (Blue Wool Scale)
EN 438-2:24	Resistance to Crazing	5 Appearance (Rating)
ASTM 638-08/ EN ISO 178	Modulus of Elasticity	≥1.85e ⁶ psi
ASTM 790-08/ EN ISO 178	Flexural Strength	≥2.87e ⁴ psi
ASTM 638-08/ EN ISO 527-2	Tensile Strength	≥2.71e ⁴ psi
ASTM 792-08/ EN ISO 1183	Density	≥86.15 lbs/ft ³

Appearance Rating: 1 = Worst - 5 = Best (no effect)

SPC Standard Grade testing results also available upon request.